

ALUJET Dichtjet

Product description

- ▶ The ALUJET Dichtjet meets the requirements of DIN 4108-7, SIA 180 and Austrian standard B8110-2. The high initial bond forms the basis for secure, extremely strong and flexible adhesion to the substrate. The ALUJET Dichtjet is a patent-free adhesive with added water and ethanol as solvents.



Fig. 1: ALUJET Dichtjet 310 ml

Product benefits

- ▶ No pressure batten required; Deep penetration into the substrate; Free from plasticisers and halogen compounds; Accelerated curing process; Also on absorbent substrates; Fresh compound can be washed off with water; adhesive according to DIN 4108-11.

Area of application

- ▶ For the airtight bonding of vapour check membranes to rising components such as plastered brickwork, concrete and wood

Technical data

Test	Standard	Unit	Value
Material			Acrylate adhesive with ethanol
Colour			Opaque blue
Temperatur resistance		°C	-40 to +100
Properties			Permanently elastic, high elasticity and adhesive strength
Consistency at 20°C			Medium viscosity/paste-like
Density			Approx. 1,0 g/cm ³
Processing temperature		°C	from -10 upwards

Specification

- ▶ Contentt: 310 ml 600 ml
- ▶ Carton content: 20 cartridges 12 Foil bag
- ▶ Palette content: 60 carton 60 carton

Storage

- ▶ in original containers above -20 ° C

Processing

▶ The ALUJET Dichtjet is applied to one side as a bead (approx. 8 mm) on a dry, dust-free and grease-free substrate, ensuring sufficient slack.

The film is then bonded to the existing component with the ALUJET Dichtjet by applying slight pressure. The adhesive bead must have a thickness of 4 mm after this bond is established. This mode of application is recommended for absorbent substrates.

In the case of less absorbent substrates, the ALUJET Dichtjet should be allowed to dry before applying the film. Wait a few moments and then press the film against the dry self-sealing adhesive. For all intents and purposes, this "dry application" is also recommended in case of vapour-tight membranes.

The curing time depends on the parameters of bead size, air humidity, temperature and absorbency of the substrate. The fresh compound can be washed off with water. Hardened adhesive can only be removed by mechanical means.



Fig.2: Connection to Components

Notes

			
<p>UN 1133</p>	<p>Please observe the safety data sheet</p>		

Our instructions for use, guidelines for use, product and service information and other technical specifications only serve as a guide, they only describe the properties of our products (value specifications/determinations at time of production) and services and do not constitute guaranteed characteristics. Owing to the wide-ranging areas of application of the individual products and the particular conditions (e.g. usage parameters, material properties etc.), it is incumbent on the user to test our products. Our applications engineering consulting - whether verbal, in writing or by way of tests is offered free of charge and is not legally binding.